



Test Report

No.SDHL2206011577HI

Date: Jul 06, 2022

Page 1 of 2

FOSHAN LEISURE TOUCH FURNITURE CO., LIMITED
NO.6 STORE, 4TH FLOOR, (QIANGFA WOOD STORE), THE EAST SIDE OF DONGCUN VILLAGE SECTION,
GUANGZHAN RD, LECONG TOWN, SHUNDE DISTRICT, FOSHAN CITY,CHINA

Sample Description : FABRIC
Style No. : 15243008-BEIGE
Item No. : 15243008-BEIGE

As above test item and its relevant information regarding to the submission are provided and confirmed by the applicant. SGS is not liable to either the test item or its relevant information, in terms of the accuracy, suitability, reliability or/and integrity accordingly.

Sample Receiving Date : Jun 10, 2022
Test Performing Date : Jun 16, 2022 to Jul 06, 2022
Test Performed : Selected test(s) as requested by applicant

Test Result Summary

No.	Test(s) Requested	Result(s)	Comments
1	Light Ageing Test-Xenon-arc Exposure ISO 4892-2:2013 and ISO 105-A02:1993 Cor2:2005	Grey scale:4-5	/
For further details, please refer to the following page(s)			

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Shunde Branch

Peter Zhao
Authorized Signatory

scan to see the report



SDHL2206011577HI



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-DocumentL.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Shunde Branch Harbin

1/F, 1st Building, European Industrial Park, No. 1 Shunhe South Road, Wusha Section, Daliang Town, Shunde, Foshan, Guangdong, China 528333 t (86-757)22805888 f (86-757)22805858 www.sgs.com.cn
中国·广东·佛山市顺德区大良街道办事处五沙顺和南路1号欧洲工业园一号楼首层 邮编: 528333 t (86-757)22805888 f (86-757)22805858 e sgs.china@sgs.com

Test Information:

Sample description: See photo

Test item: Light Ageing Test-Xenon-arc Exposure

Test method: ISO 4892-2:2013 and ISO 105-A02:1993 Cor2:2005

Test conditions:

Test cycle: ISO 4892-2:2013 cycle 1

Irradiance: $(0.51 \pm 0.02)W/(m^2 \cdot nm)@340nm$

102 min light at $(65 \pm 3)^{\circ}C$ BST, $(50 \pm 10)\%$ RH

18 min light and water spray

Filter: Daylight


Exposure period: 200h

Test Result:

Sample	Grey scale (see note)
A	4-5

Note: According to ISO 105-A02:1993/Cor.2:2005, the grey scale was determined under the D65 standard light, with scale 5 as the best and scale 1 as the worst

Photo Appendix:



End of Report

